


# Metrix Timber External Fibre Cement Flooring

MXFC offers durability, ensuring longevity in flooring applications. It provides protection against moisture, making it suitable for environments where water exposure is a concern.



## Features

- Light weight, easy to work with;
- In accordance with AS/NZS 2908.2;
- Type A, Category 4;
- Tongue & Groove for Tiled & Vinyl Application;



## Characteristic Data

Type	Details
Application	T/G Flooring or Decking
Panel Dimensions	2700 x 600 x 19mm
	<b>Tolerance</b> Length & Width: +/- 5mm Thickness: +/- 0.4mm
Straightness of Edges	Average 0.2mm/1m (Length)
Squareness of Edges	Average 0.2mm/1m
Typical Weight	28 kgs/m <sup>2</sup>

## Physical Data

### AS2908.2:2000 Cellulose-cement products - Flat sheets

Apparent Density (Dry)	1270 kg/m <sup>3</sup>
Modulus of Rupture (Wet)	16.12 MPa
Water Permeability	Nil
Frost Resistance	16.27 MPa
Warm Water	15.94 MPa
Heat-Rain	Nil Crack/Delaminatoin/Warping & Bowing or other defects.
Soak-dry	15.58 MPa

### AS1530.1-1994(R2016) - Combustibility Test

Combustibility Performance	Not Deemed Combustible.
----------------------------	-------------------------

### AS1530.3-1999 - Fire Test on Building Materials; Simultaneous determination of iginibility, flame propagation, heat release and smoke release.

Performance	Nil ignition
	Nil flame propagation
	Nil smoke
	Nil heat release

### AS4964-2004 - Method for the qualitative identification of asbestos in bulk samples

Asbestos	Absence of Asbestos
----------	---------------------

## Long Edge Sheet Join Options:

Vinyl Application



Tiled Application

