



## Metrix Timber External Fibre Cement Flooring

### Characteristic Data

Application	T/G Flooring or Decking
Panel Dimensions	2700 x 600 x 19mm
	Tolerance
	Length & Width: +/- 5mm
	Thickness: +/- 0.4mm
Straightness of Edges	Average 0.2mm/lm (Length)
Squareness of Edges	Average 0.2mm/lm
Typical Weight	28 kgs/m <sup>2</sup>

### Physical Data

#### AS2908.2:2000 Cellulose-cement products - Flat sheets

Apparent Density (Dry)	1270 kg/m <sup>3</sup>
Modulus of Rupture (Wet)	16.12 MPa
Water Permeability	Nil
Frost Resistance	16.27 MPa
Warm Water	15.94 MPa
Heat-Rain	Nil Crack/Delamination/Warping & Bowing or other defects.
Soak-dry	15.58 MPa

#### AS1530.1-1994(R2016) – Combustibility Test

Combustibility Performance	Not Deemed Combustible.
----------------------------	-------------------------

#### AS1530.3-1999 – Fire Test on Building Materials; Simultaneous determination of ignitability, flame propagation, heat release and smoke release.

Performance	Nil ignition
	Nil flame propagation
	Nil smoke
	Nil heat release

#### AS4964-2004 - Method for the qualitative identification of asbestos in bulk samples

Asbestos	Absence of Asbestos
----------	---------------------